

FORESTSTREAM®

A light weight all synthetic, non-percolating, ULC approved forestry hose for both



Applications

- Forestry extra lightweight, attack /supply hose
- Helicopter attack hose
- Urban interface, grass fire kits, and mop up hose
- Cottage and forestry home values protection hose

Features and Benefits

- · Extremely light in weight
- Unique Mertex[®] lining
- Premium all synthetic single jacket
- Available with Permatek HP™ treatment against abrasion, moisture pick up and mildew
- Resistant to most chemicals, petrol products, ozone and U.V. exposure, hydrolysis, rot and mildew
- Remains flexible to -65° F (-55° C)
- Meets or exceeds all performance requirements of NFPA 1960 (1961), Underwriters' Laboratories of Canada Spec S518.1, Factory Mutual and USDA Spec 5100-187C Type I, for 1"(25mm) and 1 ½"(38mm)
- Meets ULC requirements for S518.1.11 and can be labeled upon request in the sizes* specified below

Hose Spec	Trade Size		Bowl Size		Weight Un-coupled 100'(30.5M)		Coil Diameter 100'(30.5M)		Service Pressure		Proof Pressure		Burst Pressure	
	ln.	mm	ln.	mm	LBS	Kg	ln.	Cm.	PSI	kPa	PSI	kPa	PSI	kPa
713	1.00	25	1 5/32	29	6.5	3.0	13.5	34.3	300	2 070	600	4 140	900	6 200
715	1.5*	38*	1 11/16	43	9.5	4.3	13.5	34.3	300	2 070	600	4 140	900	6 200
718	2.50	64	2 11/16	68	16.5	7.5	15.0	38.1	250	1 725	500	3 450	750	5 175

5838 Cypihot Saint Laurent, QC Canada, H4S 1Y5

Phone 514.335.4337 Phone 877.937.9660 Fax 514.335.9633

mercedestextiles.com sales@mercedestextiles.com 1.00in/25mm



2.50in/64mm





HOW TO SPECIFY FORESTSTREAM®

THE HOSE SHALL BE SINGLE JACKET WITH SERVICE TEST PRESSURES AS SPECIFIED ON THE PREVIOUS PAGE.

JACKET

The hose jacket shall be made with high tenacity filament polyester yarn in both the warp and weft directions, to provide maximum strength to weight ratio and shall have a minimum filler (weft) yarns of 12.2 per inch (480 per Meter).

When requested the jacket shall be impregnated in one of the standard NFPA colors with high performance polymeric dispersion.

LINING

The lining (waterway) must be made from polyurethane and must be applied using a fused process that welds the polyurethane directly to the textile while the hose is being woven, without the use of adhesives or hot melt. The fused lining process must create a virtually inseparable unit without the use of adhesives, yielding an extremely low friction (pressure) loss by filling in the corrugations of the weave, creating an ultra thin and smooth waterway. Fire hose made using adhesives of any type do not meet this specification. The lining shall be approved for use with potable water.

ADHESION

The adhesion shall be such that the rate of separation of a 1 $\frac{1}{2}$ " / 38mm strip of polyurethane, transversely cut, shall not be greater than $\frac{1}{4}$ " / 6mm per minute under a weight of 12 lbs / 5.5 kg.

SERVICE, TEST, BURST PRESSURES Minimum service, test and burst pressures shall be as detailed in the specification table on the previous page.

FLOW AND FRICTION LOSS

The 1 $\frac{1}{2}$ " (38 mm) hose shall be capable of flowing 70 US GPM (264 LPM) with a maximum pressure loss of 10 PSIG (69 kPa) per 100' (30.5M).

KINK TEST

A full length will withstand a hydrostatic pressure of 600 psi / 4140 kPa while kinked.

WEIGHT

Each length of fire hose shall not weigh more than indicated in the specification table.

COUPLING SPECIFICATIONS

Couplings shall be in conformance with the current NFPA standard and made of extruded aluminum, hard coated a minimum of .002" thick. They shall be manufactured in North America and permanently labeled with country of origin.

The hose shall be available with threaded and quarter-turn threadless (QC) couplings. When quarter-turn threadless (QC) couplings are specified they shall have extended lugs to facilitate rapid connect and disconnect.

Quarter-turn threadless (QC) couplings shall be forged, approved to Standard ULC S551, and be listed & labeled. They shall be manufactured in North America and permanently labeled with country of origin.

MANUFACTURE

Both hose and couplings must be manufactured in North Americ. Couplings must be USMCA compliant.

STANDARDS

Fire hose manufactured to this specification shall meet or exceed all performance requirements of NFPA 1960 (1961), Underwriters' Laboratories of Canada Spec S518.1, 11 Factory Mutual and USDA Spec 5100-187C Type I for 1" (25mm) and $1 \frac{1}{2}$ " (38mm).

The hose shall be ULC approved and can be labeled upon request in the sizes specified*

© 2024 Mercedes Textiles Limited R10G /JH

® Represents registered trademarks of Mercedes Textiles Limited, unless otherwise noted

M Represents trademarks of Mercedes Textiles Limited, unless otherwise noted