

DIAMETERS

- 1.50in/38mm
- 1.75in/44mm

MTS-500™

Designed as a single jacket, "all purpose" industrial hose

- » Strong, compact, light in weight, and will fit on most hose storage devices
- » Unique Mertex® lining yields an extremely low friction loss, for maximum flow and superior adhesion for long life
- » Premium all synthetic single jacket
- » Available with the Identify® recessed area for color coding, bar coding and/or identification markings
- » Available with Permatek HP™ treatment against abrasion, moisture pick up and mildew
- » Resistant to most chemicals, petrol products, ozone and U.V. exposure, hydrolysis, and rot and mildew
- » Remains flexible to -65° F (-55° C)
- » Meets or exceeds all performance requirements of NFPA 1960 (1961), Underwriters Laboratories and Factory Mutual

- clear
- tan
- black
- orange
- red
- blue
- green
- yellow
- purple

Hose Spec.	Trade Size		Bowl Size		Weight Un-coupled 100' (30.5m)		Coil Diameter 100' (30.5m)		Service Pressure		Proof Pressure		Burst Pressure	
	In.	mm	In.	mm	Lbs	Kg	In.	Cm.	PSI	kPa	PSI	kPa	PSI	kPa
528	1.50	38	1 11/16	43	12.6	5.7	16.0	40.6	250	1 725	500	3 450	750	5 175
529	1.75	44	1 15/16	49	13.2	6.0	16.0	40.6	250	1 725	500	3 450	750	5 175



MERCEDES TEXTILES LIMITED

5838 Cypihot
Saint Laurent, QC
Canada, H4S 1Y5

PHONE 514.335.4337
PHONE 877.937.9660
FAX 514.335.9633

mercedestextiles.com
sales@mercedestextiles.com

HOW TO SPECIFY

MTS-500™

THE HOSE SHALL BE SINGLE JACKET WITH A SERVICE TEST PRESSURE OF 250 PSI / 1725 KPA.

.....

JACKETS

The jacket shall be made with virgin spun polyester warp yarn and a filament polyester weft yarn and shall have a minimum filler (weft) yarns of 10.4 per inch (409 per Meter).

When requested the jacket shall be impregnated in one of the standard NFPA colors with high performance polymeric dispersion.

LINING

The lining (waterway) must be made from polyurethane and must be applied using a fused process that welds the polyurethane directly to the textile while the hose is being woven, without the use of adhesives or hot melt. The fused lining process must create a virtually inseparable unit without the use of adhesives, yielding an extremely low friction (pressure) loss by filling in the corrugations of the weave, creating an ultra thin and smooth waterway. Fire hose made using adhesives of any type do not meet this specification. The lining shall be approved for use with potable water.

ADHESION

The adhesion shall be such that the rate of separation of a 1 1/2" / 38mm strip of polyurethane, transversely cut, shall not be greater than 1/4" / 6mm per minute under a weight of 12 lbs / 5.5 kg.

COLD TEMPERATURE FLEXIBILITY

The hose must remain flexible to -65°F (-55°C).

SERVICE, TEST, BURST PRESSURES

Minimum service, test and burst pressures shall be as detailed in the specification table on the previous page.

KINK TEST

A full length will withstand a hydrostatic pressure of 600 psi / 4140 kPa while kinked.

WEIGHT

Each length of fire hose shall not weigh more than indicated in the specification table.

COUPLING SPECIFICATIONS

Couplings shall be in conformance with the current NFPA standard and made of extruded aluminum, hard coated a minimum of .002" thick. The male coupling and female swivel nut must both have a recessed area to facilitate color and bar coding and/or identification markings.

They shall be manufactured in North America and permanently labeled with country of origin. They shall be expansion ring type.

STANDARDS

The hose must meet or exceed all performance requirements of NFPA 1960 (1961), Underwriters Laboratories and Factory Mutual.

The hose must also be tested in accordance with the procedures specified in "2020 UL 19 radiant heat test".

MANUFACTURE

Both hose and couplings must be manufactured in North America. Couplings must be USMCA compliant.